

# NIPPON SUPER EASY WASH

<b>Description</b>	Nippon Super Easy Wash is developed for interior use with special easy-wash property. More kinds of stains can be removed easily while the paint film still maintains its natural beauty. The wet scrub property of Nippon Super Easy Wash is much higher compared to other interior emulsion paint (more than 10,000 cycles based on Singapore Test method SS5: Part F5: 1992).
<b>Type</b>	A special modified Acrylic Polymer emulsion
<b>Uses</b>	It is ideal for interior walls and ceilings such as: - Concrete wall      - Panels              - Plaster              - Ceiling boards - Partition              - Asbestos              - Gypsum              - Fiber boards
<b>Finish</b>	Matt Colours: Wide range of attractive colours as per colour card. Special colours on request.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Less dirt &amp; stain collections;</li> <li>• Stains on Nippon Super Easy Wash can be removed easily;</li> <li>• Excellent wet scrub property (more than 10,000 cycles based on Singapore Test method SS5: Part F5: 1992);</li> <li>• Good coverage &amp; easy application</li> <li>• Anti-fungus property. Effective control against mildew growth.</li> </ul>
<b>APPLICATION DATA</b>	
<b>Surface Preparation</b>	The surface must be clean, dry and stable. <u><b>Suggested treatment:</b></u> <b>Dirt/Powder</b> : High pressure water jet wash. Clean with damp cloth. Mild detergent may be used. For very powdery surface, apply a coat of Nippon Vinilex 5170 wall Sealer. <b>Paint</b> : Unstable old film should be removed by high pressure water jet wash scraper, whichever is appropriate <b>Plaster</b> : Remove by chisel, scraper, powder grinder etc. Re-plaster to a stable surface with an approved mortar mixture. <b>Moisture</b> : High moisture causes paint defect. Observe the following level prior painting: Masonry - below 6% Wood - below 10% <b>All water sewage must be checked</b> <b>Fungus</b> : Remove by high pressure water jet wash and treat with Nippon Anti-Fungus Solution. Rinse again with clean water and dry <b>Oil or Grease</b> : Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace. Avoid painting when the humidity is more than 85%.
<b>Application Methods</b>	Brush, Roller, Air Spray or Airless spray
<b>Paint Consumption</b>	Theoretical : 10.3 m <sup>2</sup> /litre Practical : 9.8 m <sup>2</sup> /litre (at 35 microns DFT per coat after 5% loss factor)
<b>Dilution</b>	Use clean water Roller & brush : 10% maximum Airless Spray : 10% maximum Air Spray : 20% to 30%
<b>Recommended Painting System</b>	<ul style="list-style-type: none"> <li>• 1 to 2 coats Nippon Skimcoat Single Star</li> <li>• 1 coat Nippon Vinilex 5101 Wall Sealer</li> <li>• 2 coats Nippon Super Easy Wash</li> </ul>
<b>SPRAY APPLICATION</b>	<u><b>Airless Spray</b></u> Delivery Pressure (kg/cm <sup>2</sup> ) : 120 – 150 Tip Size : 0.015" at 60° angle : 0.017" at 60° or 70° angle
<b>Recommended Film Thickness</b>	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application
<b>Drying Time</b>	Surface dry: 20 minutes at 30°C
<b>Overcoating Time</b>	2 hours. Minimum based on normal conditions
<b>Cleaning</b>	Wash all equipment immediately after use with clean water

<b>Storage</b>	Reseal lid and store remaining paint in a cool, clean and dry place.
<b>Packing</b>	1 Liter, 5 Liters & 15 Liters Containers
<b>USE</b>	For an optimal easy wash effect, the paint film should be fully dried in 5 days before use. The easy-wash effect will be better if the stains are removed earlier. The stains on wall can be removed by soft tower with diluted detergent or disk washing liquid
<b>SHELF LIFE</b>	36 months from date of production as indicated on the label
<b>Precaution</b>	Avoid direct contact with sensitive skin. Use appropriate protective equipment
<b>NOTE</b>	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for the specific application, please contact Sales &amp; Marketing Dept of Nippon Paint (Vietnam) Co. Ltd. We reserve the right to modify our product data sheet without further notice.</i>