

NIPPON PAINT ECO UNDERCOAT

Economy Undercoat is a quick-drying oil-modified alkyd-based undercoat with good build.

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Solvent based	Interior & Exterior	Matt	Wood and Metal	5L

Composition

Pigment	: Titanium dioxide and mineral extenders
Binder	: Modified long oil alkyd
Thinner	: Hydrocarbon

Technical Data

Drying Time (25–30°C)	: Touch Dry : 12 minutes (Dependent on temperature and humidity)
	: Hard Dry : 2 hours (Dependent on temperature and humidity)
Overcoating Time (25–30°C)	: Minimum 8 hours (Dependent on temperature and humidity)
*Important Note: Drying Time and recoating time are strongly depending on environment ventilation, paint thickness, environment temperature, environment humidity, number of coats applied, thinner used to dilute product and recoat materials. So drying time and recoating time provided is for guide only.	
Dry Film Thickness	: Around 50 – 60 µm per coat (based on substrate condition)
No. of Coats	: 1 coat
Theoretical Coverage	: 9 – 11 m ² per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance)
Volume Solid	: ~ 52 %
Shelf Life	: Up to 12 months in tight sealed container

Application Method

Brush / Roller	: The paint is ready for use after thorough stirring. If necessary, thin down with 5% of Nippon Paint General Purpose Thinner.
	**Brushing method – Applying a slight pressure on the brush when painting will help the bristles to work the paint into the wood grains and crevices to ensure best performance of the paint film.

Recommended Coating System

Wood		
Sealer / Primer	: 9000 Aluminium Wood Primer	: 1 Coat
Intermediate	: Economy Undercoat	: 1 Coat
Top Coat	: 9000 Gloss Finish / Q-Lac Gloss Finish	: 2 Coat
Steel / Iron		
Sealer / Primer	: Red Oxide Primer	: 1 Coat
Intermediate	: Economy Undercoat	: 1 Coat
Top Coat	: 9000 Gloss Finish / Q-Lac Gloss Finish	: 2 Coat
Aluminium / Galvanized Iron		
Etching Primer	: Etching Primer 120 / Galvaprimmer	: 1 Coat
Sealer / Primer	: Red Oxide Primer	: 1 Coat
Intermediate	: Economy Undercoat	: 1 Coat
Top Coat	: 9000 Gloss Finish / Q-Lac Gloss Finish	: 2 Coat

Surface Preparation**Wood**

Surface must be dry and free from dirt, grease and other contaminants. Smoothen surface with sandpaper and then clean off and dry. The scraped areas should be spot-primed using an undercoat for wood surfaces. Light sanding on surface would ensure better subsequent intercoat adhesion.

Metal

Surface must be dry and free from dirt, grease and other contaminants. Ferrous substrate should be sanded or wire-brushed to remove mill scales and rust. Clean off dust and dry. The scraped areas should be spot-primed using a primer for metal. Light sanding on surface would ensure better subsequent intercoat adhesion.

Cleaning

Clean up equipment with thinner immediately after use.

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- During application of paint, naked flames, welding operation, and smoking should not be allowed.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose-off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

Theoretical Coverage is based on a mathematical formula and does not consider Loss Factor.

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness } (\mu)} \right] = \text{m}^2 / \text{liter} / \text{coat}$$

and does not consider LOSS FACTORS. Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.