

FEATURES

Nippon Paint Gold Paint 6000 Emulsion is a water-based paint made from premium acrylic emulsion. It is suitable for both interior and exterior walls, plaster, concrete, masonry, brick, and asbestos tile. It is used as a middle coat to cover the surface and enhance the golden color. It is weather-resistant and resistant to alkalinity in cement surfaces. It is highly washable.

- Excellent weather resistance
- Good protection against mold and algae
- Excellent adhesion

PRODUCT INFORMATION

Paint type	Matte
Product type	Acrylic water-based paint
Film appearance	Exterior and Interior
Color	shades can be selected from the catalog.
Recommended substrate	Used as a substitute for lacquer and gold leaf. plaster, concrete, brickwork, asbestos tile, and other surfaces.
Pack size	1 L & 3.75 L

TECHNICAL INFORMATION

Theoretical coverage	30 – 35	m ² /l (Depending on application, surface roughness, and porosity)
No. of coat	1	Coat
Touch dry (25–30°C)	30	mins
Recoat dry (25–30°C)	2	hours
Full cure (25–30°C)	7	day

SURFACE PREPARATION

Old Surfaces	<p>Scrub off any old, worn paint (do not use a wire brush).</p> <p>For cracked areas, repair them with Nippon Paint Vinilex Wall Putty.</p> <p>For areas with mold or algae, clean the walls with Nippon Paint Vinilex Bio Wash, a fungicide, and leave them.</p> <p>Let the walls dry for 1–2 days before applying a primer.</p>
New Surfaces	<p>must be clean and free of dust, dirt, grease, and other foreign matter. The wall should be allowed to dry for at least 28 days, with a moisture content of no more than 6% using the Kett HI-520 or 14% using the Protimeter Mini, and with a pH of no more than 8. If the surface is cracked or uneven, it is recommended to repair the cracks with a quality material or a suitable surface finish before painting.</p>

PAINT SYSTEM

Application Method	Brush & Roller
Diluted by	Clean water
Primer for skim coats and old plaster	Apply one coat of Nippon Paint Excel Primer, an oil-based primer.
Primer for new plaster	Apply one coat of Nippon Paint 5100 Wall Sealer, a water-based primer.
Middle coat	Apply one coat of Nippon Paint Gold Paint Water-based Primer.
Top Coat	Apply 2-3 coats of Nippon Paint Gold Paint Water-based Topcoat.
Application	Brush & Roller
	Dilution (%) 10 %

Note: All equipment should be cleaned immediately with Thinner after use. For Thinner, substitution of Thinner other than that approved or supplied by Nippon Paint may adversely affect product performance and void any product warranty, whether expressed or implied.

Precipitation

1. Do not apply when the relative humidity exceeds 85%. The temperature of the substrate to be applied must be 3°C higher than the dew point.
2. Do not apply at temperatures below 7°C. Otherwise, the drying and painting time will be significantly extended.
3. During application, naked flames, welding operations and smoking should not be allowed and good ventilation is necessary.

SAFETY PRECAUTIONS

1. Flammable liquid. Keep away from heat, sparks or flames.
2. Skin contact: May cause moderate skin irritation. Avoid prolonged skin contact. Wear solvent-resistant gloves. To remove spillage, use soap and water.
3. Inhalation: Respiratory irritation. Use only in well-ventilated areas. Do not breathe vapors or spray. Self-contained breathing apparatus recommended.
4. Eye contact: Causes severe eye irritation and blurred vision. Safety glasses / goggles with side shields recommended. In case of contact with eyes, rinse immediately with water and seek medical advice.
5. Ingestion: Harmful if swallowed. Keep away from food, drink and children. If swallowed, seek medical advice immediately and show container or label.
7. In case of accident, contain and collect spillage with sand or earth or absorb. Do not empty into drains or waterways.
8. Waste and empty containers should be handled and disposed of in accordance with national and local regulations. Empty containers and packaging should be taken for recycling, recovery or disposal through a suitably qualified or licensed contractor.